

## Printing materials E-2200ZC

ID: 40VM22000

### Features

- Printing materials for UV curable inkjet printers
- Transparent polyester film
- It is suitable for window display applications.
- It is high in transparency, and demonstrates excellent design.
- Provides scratch-resistant treatment on the surface
- Indoor application only


### Applications

For indoor applications

### Standard sizes

- 1,250mm × 30m rolls
- 1,560mm × 30m rolls

### Product configuration



**Face stock on the surface**  
Polyester film 50µm/transparent

**Pressure-sensitive adhesive**  
Acrylic pressure-sensitive adhesive/permanent adhesive

**Release liner**  
Release liner/polyester film

Weight: 163g/m<sup>2</sup> (Includes release liner)

### Properties

#### Adhesion (value)

Test items	Unit	Properties	Test panel	Test method
Adhesive strength 30 minutes after adhering	N/25mm	7.9	Stainless	LINTEC method
Adhesive strength 24 hours after adhering	N/25mm	9.0	Stainless	LINTEC method
Adhesive strength 30 minutes after adhering	N/25mm	10.2	Glass	LINTEC method
Adhesive strength 24 hours after adhering	N/25mm	11.4	Glass	LINTEC method
Ball tack	No.	8	—	J.Dow method
Holding strength	Second	NC 30000	Stainless	LINTEC method

#### LINTEC method

- Adhesive strength test method : Test instrument: load-cell tensile tester, release angle: 180°  
Test conditions: 23°C 50%RH, release speed: 300 mm/min  
One round trip with a rubber roller of 2kg adhesion pressure  
Test panel : Stainless panel (SUS304 #360 polishing finish)  
Float glass
- Holding strength test method : Angle: 0°, test conditions: 40°C, adhesion area: 25 mm×25 mm,  
Five round trips with a rubber roller of 2kg adhesion pressure, still load: 9.8N  
Test panel : Stainless panel (SUS304 #360 polishing finish)

- B: Base material failure   
  Cf: Cohesion failure   
  At: Adhesive transfer   
  Zip: zipping   
  NC: No creep



LINTEC Corporation *Linking your dreams*

● Head Office: 23-23 Honcho, Itabashi-ku, Tokyo 173-0001, Japan

Contact: Building & Decorative Materials Sales Dept.

Kowa Iidabashi Bldg., 2-1-2 Koraku, Bunkyo-ku,  
Tokyo 112-0004, Japan  
TEL. +81-3-3868-7733 FAX. +81-3-3868-7755  
E-mail: lag@post.lintec.co.jp

<http://www.lintec-global.com/>

## Film properties (value)

Item		Unit	Properties
Tensile strength	MD	N/25mm	96.3
	CD	N/25mm	165.1
Tensile expansion rate	MD	%	98.4
	CD	%	96.3

## Optical properties

Item	Unit	Properties
Ultraviolet ray transmission	%	5.8
Visible light transmission	%	92.3

## Precautions

- Numerical values in this data sheet are based on the results of our tests, and are not guaranteed. Please verify performance in advance according to your application.
- Use the product within one year of purchase.
- It does not provide removable performance as it is a permanent adhesive.
- To use for joints and the same surface, use the same lot.
- This film is for indoor use only.
- Please consult with us if you wish to use the product for special applications.

## Storage methods

- Avoid high temperature, low temperature and humidity for storage. Be sure to put this product in a bag, and hang it in the air. Make sure that it is not exposed to direct sunlight.
- Prevent it from being exposed to fluorescent light at close range.
- Recommended ambient temperature: 10°C-30°C, humidity: 70%RH or less  
The adhesive strength and holding strength become lower at low temperature or high temperature, and it is detached easily.
- Avoid contact with water, chemicals, and shock.

## Precautions for output and processing

- Do not touch the output surface of media directly with your hand. Sebum, oil, dirt, and scratches may lower print quality.
- Use the product as early as possible after opening.
- Output quality may differ depending on the type of printers to be used and print conditions. We recommend testing it be checked in advance.

## Precautions for install

- Install ambient temperature: 10°C-40°C  
Install at high temperature may raise the initial adhesive strength and soften products.
- Operating temperature: -30°C-80°C
- Please be fully aware of an install with soapy water. You may have difficulties in removing remaining water from the substrate and pressure-sensitive surface depending on the temperature and humidity conditions, and be unable to achieve sufficient adhesive strength. This may cause raising and detaching.
- Adhesive strength may not be achieved sufficiently depending on the properties of test panels, and raising and detaching may occur. Please check in advance.
- Adhesive strength may not be fully achieved immediately after adhering.
- The adhesive strength may not be achieved fully for install on a substrate where condensation tends to form.
- Avoid install on window films.



## Test panel

	Test panel	Install
Plastic	PP/PE/Fluorine	* 1
	ABS	○
	PET	○
	FRP	○
	Acrylic resin	* 2
	Polycarbonate	* 2
	PVC	* 3
	Tent materials	* 3
Glass	General	* 4
	Mesh included	* 4

	Test panel	Install
Metal	Galvanized steel	○
	Bonderized metal	○
	Melamine coated panel	○
	Aluminum	○
	Stainless steel	* 5
Others	Concrete	* 6
	Mortar	* 6
	Slate	* 6
	Plywood	* 6

\*1 The adhesive strength may not be fully achieved.

\*2 A bulge may occur because outgas is generated. Please consult with us in advance.

\*3 As a plasticizer and suspended particles are included, raising and detaching may occur.

\*4 Heat cracks may occur.

\*5 In case of adhering outdoors, this product may be deteriorated, depending on conditions. Please consult with us in advance.

\*6 Basically prior processes and primer coating are needed. Otherwise raising and detaching may occur due to the water oozing and adhesive failure caused by the rough surface.

\*The above 1 to 6 may differ depending on conditions. Please contact us for details.

\*If you have questions about our products, please contact us.

\*This sheet provides product information and information about the environment and safety, and does not guarantee performance or quality.

\*Product specifications and appearance are subject to change without notice for the purpose of improvement.

